

ASTM A53													
Nominal Bore	Outside Diameter		Wall Thickness		Schedule	Mass of uncoated pipe				Mass of galvanized pipe			
						P/E or T/O		T/C		P/E or T/O		T/C	
inches	inches	mm	inches	mm	No.	lb/ft	kg/m	lb/ft	kg/m	lb/ft	kg/m	lb/ft	kg/m
½	0.840	21.3	0.109	2.769	40	0.85	1.27	0.86	1.27	0.90	1.34	0.90	1.34
¾	1.050	26.7	0.113	2.870	40	1.13	1.69	1.14	1.69	1.20	1.78	1.20	1.78
1	1.315	33.4	0.133	3.378	40	1.68	2.50	1.69	2.50	1.76	2.61	1.76	2.61
1¼	1.660	42.2	0.140	3.556	40	2.27	3.39	2.23	3.40	2.38	3.54	2.38	3.55
1½	1.990	48.3	0.145	3.683	40	2.72	4.05	2.74	4.04	2.84	4.22	2.83	4.21
2	2.375	60.3	0.154	3.912	40	3.66	5.44	3.68	5.46	3.80	5.65	3.81	5.67
2½	2.875	73.0	0.203	5.156	40	5.80	8.63	5.85	8.67	5.97	8.89	6.00	8.93
3	3.500	88.9	0.216	5.486	40	7.58	11.29	7.68	11.35	7.80	11.61	7.84	11.67
3½	4.000	101.6	0.226	5.740	40	9.12	13.57	—	—	9.36	13.93	—	—
4	4.500	114.3	0.237	6.020	40	10.80	16.07	10.92	16.23	11.08	16.48	11.18	16.64
5	5.563	141.3	0.258	6.553	40	14.63	21.77	14.90	22.07	14.97	22.28	15.17	22.58
6	6.625	168.3	0.280	7.112	40	18.99	28.26	19.34	28.58	19.40	28.87	19.62	29.19

P/E Plain end  
 T/O Threaded only  
 T/C Threaded and coupled

Notes:

- 1 Pipe supplied square cut or bevelled. Bevelled from 1¼" to 6".
- 2 RoborTube can also manufacture lighter wall thicknesses than Schedule 40 in outside diameters between ½" to 8"
- 3 Pipes can be supplied in either grade A or grade B (Modified - weld seam not annealed)
- 4 Pipes can be supplied galvanized as per specification.