

ASTMA795 Schedule 10 and 30											
Nominal Bore	Outside Diameter		Wall Thickness		Schedule	Mass of uncoated		Mass of galvanized		Mass galvanized T/C	
	inches	mm	inches	mm		No.	lb/ft	kg/m	lb/ft	kg/m	lb/ft
3/4	1.050	26.7	0.083	2.11	10	0.86	1.28	0.91	1.35	0.92	1.36
1	1.315	33.4	0.109	2.77	10	1.41	2.09	1.47	2.18	1.48	2.21
1 1/4	1.660	42.2	0.109	2.77	10	1.81	2.69	1.88	2.80	1.91	2.85
1 1/2	1.900	48.3	0.109	2.77	10	2.09	3.11	2.18	3.24	2.22	3.30
2	2.375	60.3	0.109	2.77	10	2.64	3.93	2.75	4.10	2.83	4.21
2 1/2	2.875	73.0	0.120	3.05	10	3.53	5.26	3.67	5.46	3.76	5.59
3	3.500	88.9	0.120	3.05	10	4.34	6.46	4.51	6.71	4.62	6.88
3 1/2	4.000	101.6	0.120	3.05	10	4.98	7.41	5.17	7.70	-	-
4	4.500	114.3	0.120	3.05	10	5.62	8.37	5.84	8.69	6.09	9.06
5	5.563	141.3	0.134	3.40	10	7.78	11.58	8.05	11.98	8.42	12.54
6	6.625	168.3	0.134	3.40	10	9.30	13.85	9.63	14.33	10.14	15.09
8	8.625	219.1	0.188	4.78	10	16.96	25.26	17.39	25.88	-	-
8	8.625	219.1	0.277	7.04	30	24.72	36.82	25.16	37.44	-	-

T/C Threaded and coupled

Notes:

- 1 Pipes can be supplied in either grade A or grade B (Modified - weld seam not annealed)
- 2 Pipe supplied square cut or bevelled. Bevelled from 1 1/4" to 8".

ASTM 795 Schedule 40											
Nominal Bore	Outside Diameter		Wall Thickness		Schedule	Mass of uncoated		Mass of galvanized		Mass galvanized SS	
	inches	mm	inches	mm		No.	lb/ft	kg/m	lb/ft	kg/m	lb/ft
1/2	0.840	21.3	0.109	2.77	40	0.85	1.27	0.89	1.32	0.89	1.32
3/4	1.050	26.7	0.113	2.87	40	1.13	1.69	1.18	1.76	1.18	1.75
1	1.315	33.4	0.133	3.38	40	1.68	2.50	1.74	2.59	1.74	2.59
1 1/4	1.660	42.2	0.140	3.56	40	2.27	3.39	2.35	3.50	2.36	3.51
1 1/2	1.900	48.3	0.145	3.68	40	2.72	4.05	2.81	4.18	2.82	4.20
2	2.375	60.3	0.154	3.91	40	3.66	5.45	3.77	5.61	3.81	5.66
2 1/2	2.875	73.0	0.203	5.16	40	5.80	8.64	5.94	8.84	5.97	8.88
3	3.500	88.9	0.216	5.49	40	7.58	11.29	7.75	11.53	7.78	11.59
3 1/2	4.000	101.6	0.226	5.74	40	9.12	13.58	9.31	13.85	-	-
4"	4.500	114.3	0.237	6.02	40	10.80	16.09	11.02	16.41	11.13	16.57

T/C Threaded and coupled

Notes:

- 1 Pipes can be supplied in either grade A or grade B (Modified - weld seam not annealed)
- 2 Pipe supplied square cut or bevelled. Bevelled from 1 1/4" to 8".