

Light								
		Size			Mass of painted or uncoated pipe		Mass of galvanized pipe	
Nominal Bore	Nominal Size	Outside Diameter		Wall Thickness	P/E or T/O	T/C	P/E or T/O	T/C
mm	inches	Min (mm)	Max (mm)	mm	kg/m	kg/m	kg/m	kg/m
15	½	21.0	21.4	2.0	0.947	0.956	1.00	1.01
20	¾	26.4	26.9	2.3	1.38	1.39	1.45	1.46
25	1	33.2	33.8	2.6	1.98	2.00	2.07	2.09
32	1¼	41.9	42.5	2.6	2.54	2.57	2.65	2.68
40	1½	47.8	48.4	2.9	3.23	3.27	3.36	3.40
50	2	59.6	60.2	2.9	4.08	4.15	4.23	4.30
65	2½	75.2	76.0	3.2	5.71	5.83	5.91	6.03
80	3	87.9	88.7	3.2	6.72	6.89	6.95	7.12
100	4	113.0	113.9	3.6	9.75	10.0	10.1	10.3

Medium								
		Size			Mass of painted or uncoated pipe		Mass of galvanized pipe	
Nominal Bore	Nominal Size	Outside Diameter		Wall Thickness	P/E or T/O	T/C	P/E or T/O	T/C
mm	inches	Min (mm)	Max (mm)	mm	kg/m	kg/m	kg/m	kg/m
15	½	21.1	21.7	2.6	1.21	1.22	1.26	1.27
20	¾	26.6	27.2	2.6	1.56	1.57	1.62	1.63
25	1	33.4	34.2	3.2	2.41	2.43	2.50	2.52
32	1¼	42.1	42.9	3.2	3.10	3.13	3.21	3.24
40	1½	48.0	48.8	3.2	3.57	3.61	3.69	3.73
50	2	59.8	60.8	3.6	5.03	5.10	5.19	5.26
65	2½	75.4	76.6	3.6	6.43	6.55	6.62	6.74
80	3	88.1	89.5	4.0	8.37	8.54	8.60	8.77
100	4	113.3	114.9	4.5	12.2	12.5	12.5	12.8
125	5	138.7	140.6	5.0	16.6	17.1	17.0	17.5
150	6	164.1	166.1	5.0	19.7	20.3	20.2	20.8

Heavy								
		Size			Mass of painted or uncoated pipe		Mass of galvanized pipe	
Nominal Bore	Nominal Size	Outside Diameter		Wall Thickness	P/E or T/O	T/C	P/E or T/O	T/C
mm	inches	Min (mm)	Max (mm)	mm	kg/m	kg/m	kg/m	kg/m
15	½	21.1	21.7	3.2	1.44	1.45	1.49	1.50
20	¾	26.6	27.2	3.2	1.87	1.88	1.93	1.94
25	1	33.4	34.2	4.0	2.94	2.96	3.02	3.04
32	1¼	42.1	42.9	4.0	3.80	3.83	3.90	3.93
40	1½	48.0	48.8	4.0	4.38	4.42	4.50	4.54
50	2	59.8	60.8	4.5	6.19	6.26	6.34	6.41
65	2½	75.4	76.6	4.5	7.93	8.05	8.13	8.25
80	3	88.1	89.5	5.0	10.3	10.5	10.6	10.8
100	4	113.3	114.9	5.4	14.5	14.8	14.8	15.1
125	5	138.7	140.6	5.4	17.9	18.4	18.2	18.7
150	6	164.1	166.1	5.4	21.3	21.9	21.7	22.3

P/E Plain end
 T/O Threaded only
 T/C Threaded and coupled

Notes:
 1. Threading conforms to BS 21
 2. Pipes galvanized to EN 10240 or ISO 1461 whichever applicable