

Size			Mass of painted or uncoated pipe	Mass of galvanized pipe
Nominal Bore *	Outside Diameter	Wall Thickness	P/E	P/E
mm	mm	mm	kg/m	kg/m
15	21.2	1.8	0.861	0.914
20	26.7	2.1	1.27	1.34
25	33.5	2.4	1.84	1.93
32	42.2	2.4	2.36	2.46
40	48.1	2.6	2.92	3.04
50	59.9	2.6	3.67	3.83
	60.3	1.6	2.32	2.48
	73.0	3.0	5.18	5.37
65	75.6	3.0	5.37	5.57
80	88.3	3.0	6.31	6.54
	101.6	2.0	4.91	5.18
100	113.5	3.3	8.97	9.27
	114.3	2.0	5.54	5.84
	139.7	3.5	11.8	12.1
	141.3	2.8	9.56	9.94
	165.1	2.8	11.2	11.6
	168.3	3.0	12.2	12.7
	219.1	3.5	18.6	19.2

\* previously SABS/SANS 62 light

P/E Plain end

Notes:

- 1 The tubes in this series are supplied in standard length of 6m (other lengths can be supplied on request)
- 2 Material specification:

Yield MPa (min)	Tensile MPa (min)	Min elong. %	C % max	Mn % max	Si %	P % max	S % max
200	300	15.0	0.22	1.6	< .040%	0.025	0.020

- 3 Pipes galvanized to EN10240 or ISO 1461 whichever applicable
- 4 Other sizes and thicknesses are available on request
- 5 Only supplied plain ends